

SILVERBACK™ GASKETS



- Superior blend of PTFE and 316 stainless steel
- Excellent chemical resistance
- Non-stick surfaces
- USP Class VI compliant

 **NEWMAN™**
SANITARY GASKET COMPANY

PRODUCTS OF INTEGRITY...FROM PEOPLE OF INTEGRITY

SILVERBACK™

The PTFE and Stainless Steel Gasket

This special blend of 50/50, PTFE and 316 passivated stainless steel has been tested and proven to add stability and longevity to your process piping systems. These new components are especially useful in S.I.P. systems preventing downtime and lowering maintenance needs.



SILVERBACK™ is the strongest compound on the market today.

SILVERBACK™ easily outperforms standard gaskets made with Teflon® under even the most demanding pharmaceutical applications. In fact, SILVERBACK™ lasts up to five times longer in most applications.

Prevents System Downtime

The unparalleled strength of SILVERBACK™ eliminates maintenance needs and helps prevent system downtime by eliminating cold flow creep. This makes SILVERBACK™ ideal for sanitary steam pipe connections in both extreme cold (down to -20°F) and hot conditions (up to 450°F). SILVERBACK™ gaskets are available in standard sizes, from 1/2" to 12" diameter, to service virtually any S.I.P. application.

Newman's SILVERBACK™ is tough under S.I.P. conditions:

- Superior creep resistance
- Minimal thermal expansion
- Excellent chemical resistance
- No pigmentation
- Passivated to eliminate rouging
- Stops leaks when torqued correctly (50 in./lbs.)
- No gasket extrusion into the sanitary tube I.D.
- No obstruction of flow
- Non-stick surfaces
- Excellent expansion and contraction stability
- I.D. Pharmaceutical finish

Meets High Pharmaceutical Standards

- USP Class VI
- Cytotoxicity Criteria
- ASME-BPE Standards

Available in Sizes:

1/2", 3/4", 1", 1 1/2", 2", 2 1/2", 3", 4", 6", 8", 10" and 12"

| PROPERTY | ASTM METHOD | VALUE |
|-------------------------|-------------|---------|
| Specific Gravity | D792 | 3.30 |
| Tensile Strength | D4894 | 2791psi |
| Elongation @ Break | D4894 | 207% |
| Compressive Stress @ 1% | D695 | 832 |
| Compressive Stress @ 5% | D695 | 2590 |
| Hardness | D2240 | 68 |
| Temperature Low | Continuous | -20° F |
| Temperature High | Continuous | 450° F |

® Teflon is a registered trademark of DuPont.

™ Silverback is a trademark of Newman Sanitary Gasket Company



P.O. Box 222, Lebanon, Ohio 45036 • Telephone (513)932-7379 • Fax (513)932-4493
www.newmangasket.com • e-mail: customer@newmangasket.com