



HOW OUR PARTS LINE UP



Liner Material	AR400-AR600 Steels	Chromium Carbide Overlay	White Iron Castings	Si-Tec® Composites
Hardness (resistance to sliding abrasion)	23 - 56 Rc	56 - 59 Rc	56 - 63 Rc	82 Rc (Ceramic) 56 - 63 Rc (Matrix)
Impact Resistance	High	Low	Medium	Medium
Variety of Shapes	Rectangular or rolled	Flat	Any	Any
Thicknesses	Limited to mill offerings	Limited to mill offerings	Variable >12mm to 450mm	Variable >50mm to 450mm
Other Considerations		Overlay may be susceptible to cracking		

Please contact us for more information and quotes:

(509)921-8879 • www.SpokaneIndustries.com • LHagmann@SpokaneIndustries.com

Registered in the U.S. Patent and Trademark Office